

PURAQUA™ CLC 60 Coal Based Pellet Activated Carbon

PURAQUA™ CLC 60 is a high activity extruded activated carbon made by steam activated process of selected grades of anthracite coal. Higher mechanical hardness and excellent proportion of micropores and macropores makes PURAQUA™ CLC 60 ideal choice for number of applications in air and gas treatment. It is very effective in the recovery of solvents and purifications of industrial and natural gas.

SPECIFICATIONS

Iodine Number (mg/g) (Min.)	950
Carbon Tetrachloride Adsorption (%)	60
Hardness (%) (Min.)	95
Ash content (%) (Max.)	12
Moisture Content (%) (Max.)	5
Density (Gm/Liter)	450 – 500
pH	8 – 10

APPLICATIONS

- Waste incineration
- Recovery of solvents
- Purifications of industrial and natural gas streams

FEATURES

- High adsorption kinetics
- Excellent hardness
- Excellent proportion of micropores and macropores

DIAMETER SIZE

0.8 mm — 5.0 mm

PACKAGING

- 25 Kg/ 50 Kg Bag
- 500 Kg/ 1000 Kg Jumbo Bag
- 1 Cubic feet Bag
- Customized packing available

